

Nelco Advanced Circuitry Materials

Nelco® N4000-13 Nelco® N4000-13 SI®



High-Speed Multifunctional Epoxy Laminate & Prepreg

The Nelco® N4000-13 series is an enhanced epoxy resin system engineered to provide both outstanding thermal and high signal speed / low signal loss properties. N4000-13 SI® is excellent for applications that require optimum signal integrity and precise impedance control, while maintaining high reliability through CAF² and thermal resistance.

Key Features

Lead-Free Assembly Compatible

- Ideally suited for assemblies with a maximum reflow temperature of 245°C¹
- Nelco N4000-13 has shown acceptable results in reflow conditions up to 260°C¹ depending on the PCB design and manufacturing processing

T_g >210°C, outstanding thermal, electrical and signal loss properties

- Excellent thickness control for tight tolerance impedance applications
- Low Df and Dk allows for low signal distortion and faster signal propagation required by high frequency (1 - 10 GHz) and high reliability applications

CAF² Resistant

- The low Z-CTE and proven CAF resistance² provide long-term reliability for both RF and digital applications

Signal Integrity and Buried Capacitance™ Options

- When used, SI glass provides enhanced electrical performance for even the most demanding applications
- Approved ZBC-2000® substrate available for thinner, more reliable assemblies and increased board densities

High-T_g FR-4 processing

- Processes similar to traditional high T_g FR-4 materials
- 90 min press at 193°C and 275-350 psi

Available in a variety of constructions

- Vacuum laminated
- Available in a wide variety of constructions, copper weights and glass styles including standard copper, double treat and RTFOIL® laminate.
- Meets UL 94V-0 and IPC-4101/29 specifications
- All Nelco® materials are RoHS compliant.

Applications

- Fine-Line Multilayers
- Backplanes
- Surface-Mount Multilayers
- BGA Multilayers
- MCM-Ls
- CSP Attachment
- Wireless Communication Infrastructure
- High Speed Services
- High Speed Storage Networks
- Internet Switching / Routing Systems

Global Availability

Nelco, California	+1.714.879.4293
Nelco, New York	+1.845.567.6200
Neltec, Arizona	+1.480.967.5600
Nelco, Asia Pacific	+65.6861.7117
Neltec Europe SAS	+33.380.10.10.00
Neltec, SA	+33.562.98.52.90
www.parkelectro.com	info@parkelectro.com

Park's UL file number: E36295

Nelco N4000-13 and N4000-13 SI®

High-Speed Multifunctional Epoxy Laminate & Prepreg

	N4000-13	-13 SI	U.S. Units	N4000-13	-13 SI	Metric	Test Method
Mechanical Properties							
Peel Strength - 1 oz. (35 micron) Cu							
After Solder Float	7.5	7.5	lb/inch	1.31	1.31	N/mm	IPC-TM-650.2.4.8
At Elevated Temperature	8.1	8.1	lb/inch	1.42	1.42	N/mm	IPC-TM-650.2.4.8.2a
After Exposure to Process Solutions	9.0	9.0	lb/inch	1.58	1.58	N/mm	IPC-TM-650.2.4.8
X/Y CTE [-40°C to +125°C]	10 - 14	9 - 13	ppm/°C	10 - 14	9 - 13	ppm/°C	IPC-TM-650.2.4.41
Z Axis CTE Alpha 1 [50°C to Tg]	70	70	ppm/°C	70	70	ppm/°C	IPC-TM-650.2.4.41
Z Axis CTE Alpha 2 [Tg to 260°C]	280	280	ppm/°C	280	280	ppm/°C	IPC-TM-650.2.4.41
Z Axis Expansion [50°C to 260°C]	3.5	3.5	%	3.5	3.5	%	IPC-TM-650.2.4.41
Young's Modulus (X/Y)	4.2/3.3	2.4/2.3	psi x 10 ⁶	28.5/22.4	16.5/15.9	GN/m ²	ASTM D3039
Poisson's Ratios (X/Y)	0.13/0.11	0.18/0.17		0.13/0.11	0.18/0.17		ASTM D3039
Thermal Conductivity	0.350	0.294	W/mK	0.350	0.294	W/mK	ASTM E1461
Specific Heat	1.20	1.30	J/gK	1.20	1.30	J/gK	ASTM E1461
Electrical Properties							
Dielectric Constant (50% resin content)							
@ 1 GHz (RF Impedance)	3.7	3.4		3.7	3.4		IPC-TM-650.2.5.5.9
@ 2.5 GHz (Split Post Cavity)	3.7	3.2		3.7	3.2		
@ 10 GHz (Stripline)	3.6	3.2		3.6	3.2		IPC-TM-650.2.5.5.5
@ 10 GHz (Split Post Cavity)	3.7	3.3		3.7	3.3		
Dissipation Factor (50% resin content)							
@ 2.5 GHz (Split Post Cavity)	0.009	0.008		0.009	0.008		
@ 10 GHz (Stripline)	0.009	0.008		0.009	0.008		IPC-TM-650.2.5.5.5
@ 10 GHz (Split Post Cavity)	0.008	0.007		0.008	0.007		
Volume Resistivity							
C - 96/35/90	10 ⁸	10 ⁸	Mμ - cm	10 ⁸	10 ⁸	Mμ - cm	IPC-TM-650.2.5.17.1
E - 24/125	10 ⁷	10 ⁸	Mμ - cm	10 ⁷	10 ⁸	Mμ - cm	IPC-TM-650.2.5.17.1
Surface Resistivity							
C - 96/35/90	10 ⁷	10 ⁷	Mμ	10 ⁷	10 ⁷	Mμ	IPC-TM-650.2.5.17.1
E - 24/125	10 ⁷	10 ⁷	Mμ	10 ⁷	10 ⁷	Mμ	IPC-TM-650.2.5.17.1
Electric Strength	1200	1000	V/mil	4.7x10 ⁴	3.9x10 ⁴	V/mm	IPC-TM-650.2.5.6.2
Dielectric Breakdown	>50	>50	kV	>50	>50	kV	IPC-TM-650.2.5.6
Arc Resistance	123	123	seconds	123	123	seconds	IPC-TM-650.2.5.1
Thermal Properties							
Glass Transition Temperature (Tg)							
DSC (°C)	210	210	°C	210	210	°C	IPC-TM-650.2.4.25c
TMA (°C)	200	200	°C	200	200	°C	IPC-TM-650.2.4.24c
DMA (°C) (Tan d Peak)	240	240	°C	240	240	°C	IPC-TM-650.2.4.24.3
Degradation Temp (TGA) (5% wt. loss)	350	350	°C	350	350	°C	IPC-TM-650.2.4.24.6
Pressure Cooker-60 min then solder dip							IPC-TM-650.2.6.16
@288°C until failure (max 10 min.)	Pass	Pass		Pass	Pass		(modified)
T260	30+	30+	minutes	30+	30+	minutes	IPC-TM-650.2.4.24.1
T288	10+	10+	minutes	10+	10+	minutes	IPC-TM-650.2.4.24.1
Chemical/Physical Properties							
Moisture Absorption	0.1	0.1	wt. %	0.1	0.1	wt. %	IPC-TM-650.2.6.2.1
Methylene Chloride Resistance	0.7	0.7	% wt. chg.	0.7	0.7	% wt. chg.	IPC-TM-650.2.3.4.3
Density [50% resin content]	1.91	1.79	g/cm ³	1.91	1.79	g/cm ³	Internal Method

Park Electrochemical Corp. is a global advanced materials company which develops and manufactures high-technology digital and RF/microwave printed circuit materials and advanced composite materials. The company operates under the Nelco®, Nelcote® and Nova™ names. All test data provided are typical values and not intended to be specification values. For review of critical specification tolerances, please contact a Nelco representative directly. Nelco reserves the right to change these typical values as a natural process of refining our testing equipment and techniques. Nelco reserves the right to make changes without further notice to any products herein to improve reliability, function or design. Nelco does not assume any liability arising out of the application or use of any product described herein; neither does it convey any license under its patent rights nor the rights of others. This disclaimer of warranty is in lieu of all warranties whether expressed, implied or statutory, including implied warranties of merchantability or fitness for a particular purpose.

Nelco®, Neltec®, Nelcote®, Nova™, RTFoil®, SI®, LD® and EF® are trademarks of Park Electrochemical Corp. BC®, ZBC-2000® and Buried Capacitance™ are Trademarks of the Sanmina-SCI Corporation.

¹Refer to the [N4000-13 Best Practices](#) document and [Contract Manufacturing Q&A](#) for PCB processing recommendations. Visit www.parkelco.com for more information.²CAF resistance has been established to greater than 500 hours using a specific OEM coupon design and test procedure. Visit www.parkelco.com for more information.